

## TEST REPORT

No. : GZIN1604018212PS-01

Date : May 25, 2016

Page: 1 of 4

CUSTOMER NAME: SAN SIAM INDUSTRY CO.,LTD  
ADDRESS: 189/313 MOO.5 PANTHAI-NORASING,MUEANG,SAMUTSAKHON  
74000 THAILAND

The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : POLYESTER PVC MESH SHEET  
SGS Ref. No. : GZIN1604018170PC, GZIN1604018349MR  
Product Specification : 1000D × 1000D 14 × 14, 270g/m<sup>2</sup>  
Date of Receipt : Apr 29, 2016  
Testing Start Date : Apr 29, 2016  
Testing End Date : May 06, 2016  
Test result(s) : For further details, please refer to the following page(s)

# TEST REPORT

No. : GZIN1604018212PS-01

Date : May 25, 2016


Page: 2 of 4

## Summary of Results:

No.	Test Item	Test Method	Result			Conclusion
			Maximum Tensile Force	X direction	Y direction	
1	Tensile Test	DIN 53354:1981	Maximum Tensile Force	X direction	2010 N	/
				Y direction	1930 N	
			Elongation at Break	X direction	26 %	
				Y direction	25 %	

Note: Pass : Meet the requirements;  
Fail : Does not meet the requirements;  
/ : Not Apply to the judgment.

## Original Sample Photo:



# TEST REPORT

No. : GZIN1604018212PS-01

Date : May 25, 2016

Page: 3 of 4

Test Item: Tensile Test

Sample Description: See photo

Test Method: DIN 53354:1981

Test Condition:

Specimen width: 50 mm

Testing speed: 100 mm/min

Grip separation: 100 mm


Lab Environmental Condition:  $23 \pm 2$  °C,  $50 \pm 5$  % RH

Test Result:

Test Item	Test Result	
	Maximum Tensile Force	X direction
Y direction		1930 N
Elongation at Break	X direction	26 %
	Y direction	25 %

Note: Test specimens were cut from the sample.

Test Photo:




# TEST REPORT

No. : GZIN1604018212PS-01

Date : May 25, 2016

Page: 4 of 4



## Equipment Information:

Equipment	Model	Equipment No.	Calibration date	Next Calibration date
Universal Testing Machine	Z030	GZMR-PL-E140	2015-11-18	2016-11-17

## Appendix Information:

This test report supersedes test report No. GZIN1604018212PS, the original test report is void.

\*\*\*\*\* End of report\*\*\*\*\*